

Cee-Bee[®] A-292NC-M

Cee-Bee[®] A-292NC-M is an extremely versatile, thickened paint stripper which rapidly and safely strips alkyd and modified alkyd enamels, nitrocellulose and acrylic lacquers, most moisture cured polyurethanes and many air-dried epoxy coatings. Application is either by Spray or Brushing on the surface.

Conforms To

- AMS
 - AMS 1375A
- Goodrich
 - CMM 32-40-50
- Goodrich & Messier
 - CMM32-41-83
- IAE
 - Omat 01-140A
- Military
 - TT-R-248B

Benefits

- Rapidly strips a wide variety of coatings and primers.
- Contains no phenolics or cyanides, or chrome.
- Safe on all common aircraft structural metals, including: aluminum and aluminum alloys, magnesium and magnesium alloys, cadmium plating, mild steel and high strength steel.
- Thixotropic - clings to inclined, vertical and overhead surfaces,
- Effective over a wide range of temperatures from 40 - 100°F (50 - 38°C).
- Readily removes carbon deposits from bare metal surfaces.

Properties

- Thick, hazy yellow liquid
- Pungent odor
- pH 12
- Low toxicity

Notes Prior to Handling

Before using your Cee-Bee[®] products, all safety and operating instructions should be read and understood. If you have any questions, please contact your Cee-Bee[®] representative before proceeding.

Use Procedure

Paint Stripping

1. Surface should be dry and below 100°F (38°C).
 - a. The optimum stripping temperature is 65 - 85°F (18 - 30°C).
2. Apply a very thin, uniform film of Cee-Bee[®] A-292NC-M with brush, roller or non-atomizing spray.
3. When the coating begins to absorb the stripper, apply another uniform film.
4. Allow the stripper to dwell until the coating is loosened from the substrate.
5. Agitate with a stiff bristle brush and reapply the stripper to areas not completely released.
6. When stripping action is complete, squeegee or scrape off loosened coating and excess stripper and collect for disposal.
7. Rinse with high-pressure water to remove paint and stripper residues.

Carbon Removal from Unpainted Metals

1. Surface should be dry and below 100°F (38°C).
2. Apply a very thin, uniform film of Cee-Bee[®] A-292NC-M with brush, roller or non-atomizing spray.
3. When the coating begins to absorb the stripper, apply another uniform film.
4. Allow the stripper to dwell until the coating is loosened from the substrate.
5. Agitate with a stiff bristle brush.
6. Rinse with flowing water. Do not allow stripper or rinse water to contact any adjacent painted area.

Safety, Handling, and Precautions

- Use with good ventilation. Do not use in closed spaces.
- Avoid contact with eyes and skin. Wear gloves and goggles or face shield. Use full rack gear for large-scale operation.
- In case of accidental contact with eyes or skin, flood area with water. Seek medical attention if irritation persists.
- May damage acrylic plastic and electrical wiring insulation.
- Prolonged contact with copper alloys may result in surface staining.

Contact Us

United States

McGean

Phone: +1-216-441-4900

Fax: +1-216-441-1377

Email: Aviation@McGean.com

United Kingdom

McGean-Rohco (UK) Ltd.

Phone: +44-1902-456563

Fax: +44-1902-457443

Email: Aviation@McGean-Rohco.co.uk

Singapore

McGean Singapore

Phone: +65-6863-2296

Fax: +65-6863-2297

Email: Info@ceebee.com.sg

China

Cee-Bee Aviation Materials (Xiamen) Co. Ltd.

Phone: +86-592-551-3689

Email: Info@ceebee.com.cn

Cee-Bee® A-292NC-M is an extremely versatile, thickened paint stripper which rapidly and safely strips alkyd and modified alkyd enamels, nitrocellulose and acrylic lacquers, most moisture cured polyurethanes and many air-dried epoxy coatings. Application is either by Spray or Brushing on the surface.

CAUTION: BEFORE USING ANY OF THESE PRODUCTS, YOU MUST BECOME COMPLETELY FAMILIAR WITH THE INFORMATION CONTAINED IN MCGEAN'S SAFETY DATA SHEETS. All information contained therein or in this document regarding handling, personal protection, and other safety measures must be followed during use. McGean presents the information herein without warranty and disclaims any liability, including any consequential, special, or indirect damages, arising from its use and misuse. Because the use, the conditions of use, product or product composition, and/or applicable laws may differ from one location to another and/or may change with time, the purchaser and/or user is solely responsible for determining whether the product is appropriate for use. McGean recommends use of this product solely in commercial processes which are specified by McGean and which do not violate any third-party patent rights or any laws or regulations or otherwise adversely impact human health and the environment. Users must make their own investigations and determine the suitability of the product for their particular purposes. McGean does not guarantee the accuracy of any data provided by its suppliers. MCGEAN MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE EXCEPT AS EXPRESSLY STATED IN THE SELLER'S SALES CONTRACT OR SALES ACKNOWLEDGEMENT FORM. USE OF ANY MCGEAN PRODUCT IS AT THE USER'S RISK.



Revision: 06/2021