



Penetrant Professor Approved

Product Data Sheet

FBP-913

Fluorescent Penetrant



Met-L-Chek manufactures a complete line of penetrants used in the fluorescent (Type 1) and visible (Type 2) dye penetrant inspection process. All Met-L-Chek penetrants are qualified to AMS-2644 and are sold under the Met-L-Chek® and Pen-Chek® trademarks.

FBP-913 is approved to AMS-2644 as a fluorescent (Type 1); Methods "A", and "C"; sensitivity level 3 water washable inspection penetrant. For Method "C" applications it is used with E-59, E-59A, R-503, and R-504. FBP-913 is applied by immersion, spray, or wipe on. It is approved for high sensitivity aerospace applications.

FBP-913 is listed on the Qualified Products List for AMS-2644. It meets the requirements of AMS-2647, ASME Boiler and Pressure Vessel Code Section V, ASTM E-165, and ASTM E-1417, for penetrant inspection materials. It is low in sulfur and halogens and is safe for use on all metal surfaces.


FBP-913 is a special oil and solvent free formulation which utilizes biodegradable components, and is VOC free.

Guide to METHOD "A" processing per ASTM E-1417

Guide to METHOD "C" (wipe off) processing per ASTM E-1417

- 1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°- 125°F) before penetrant is applied.
2. Apply FBP-913 penetrant using spray, immersion, or wipe on.
3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
4. Wash part; water temperature 10°-38°C (50°-100 °F). Water pressure < 275kPa (< 40 psi); if a hydro-air nozzle is used, limit pressure to < 172kPa (< 25 psi). Distance > 30cm (> 12 inches). Wash time- only long enough to remove surface fluorescence under UV-A (black light) .
5*. Dry part; temperature not to exceed 71°C (160°F), time - only long enough to dry surface.
6. Apply dry powder developer, form "a" (D-72A), by dusting, or non aqueous developer, form "d"(D-70), by spraying.
6A*. If water based developer form "c"(D-78B) is used it is applied by immersion or spray, prior to step 5 drying.
7. Wait a minimum of 10 minutes before inspection. Maximum time is 1 hour for form "d " (non aqueous) and maximum 4 hours for form "a" (dry powder). If times are exceeded, clean part and reprocess.
8. Use UV-A illumination of >1000 μW/cm² @ 15 inches (38.1 cm) in a darkened area of < 21 lux visible light (< 2 foot candles).

- 1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°- 125°F) before penetrant is applied.
2. Apply FBP-913 penetrant using spray, immersion, or wipe on.
3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
4. Moisten cloth with E-59, E-59A, R-503 or R-504 and wipe penetrant from surface. Do not spray remover on surface to remove penetrant, as sensitivity will be impaired. Water may be used to wipe FBP-913 from the surface, but the surface must be dried before developer is applied.
5. Apply dry powder developer D-72A by dusting, or non aqueous developer D-70 by spraying.
6. Wait a minimum of 10 minutes before inspection.
7. Inspect under UV-A illumination of >1000 μW/cm² @ 15 inches (38.1 cm) in a darkened area of < 21 lux visible light (< 2 footcandles).



FBP-913

Fluorescent penetrant indications on grinding cracks



Penetrant Professor Approved

Product Data Sheet

FBP-913

Fluorescent Penetrant



Typical Physical Properties

Form: clear yellow green viscous liquid Density: 975 g/L
 Flash Point: > 93°C (> 200°F)
 Viscosity 26.4 mm²/s
 Water Tolerance:> 20 %
 Water Content: < 1 %
 Fluorescent Brightness: (AMS-2644 requirement > 90 %)
 127.3%Corrosion of aluminum: none
 Corrosion of carbon steel: none
 Corrosion of magnesium: none
 Corrosion of stainless steel: none
 Corrosion of titanium: none
 Chloride content: < 100 ppm (0.01%)
 Fluoride content: < 50 ppm (0.005%)
 Sodium content: < 100 ppm (0.01%)
 Sulfur content: < 100 ppm (0.01%)
 Mercury: none
 VOC's: 0 g/L
 Ozone layer depleting substances: none
 PCB's: none

Product Availability

6 x 1 pint (0.4L) can with dauber
 1 gallon (3.7L) plastic bottle
 5 gallon (18.9L) plastic jug with our spout
 55 gallon (208L) plastic drum

NSN

1 gallon	6850-01-263-8430
5 gallon	6850-01-263-2263
55 gallon	6850-01-263-4056

Specifications

- | | |
|------------------------------------|--------------------|
| ISO 3452 | |
| AMS 2644 | AMS 2647 |
| ASTM E-1417 | ASTM E-165 |
| BAC 5423 | GE P3TF2 |
| MIL-STD-2132 | MIL-STD-271 |
| R-R RPS-702 | R-R CSS-232 |
| ASME B & PV code Sec. V | |
| NAVSEA T9074-AS-GIB-010/271 | |



BEFORE USING ANY OF THESE PRODUCTS, YOU MUST BECOME COMPLETELY FAMILIAR WITH THE INFORMATION CONTAINED IN MCGEAN'S SAFETY DATA SHEETS. All information contained therein or in this document regarding handling, personal protection, and other safety measures must be followed during use. McGean presents the information herein without warranty and disclaims any liability, including any consequential, special, or indirect damages, arising from its use and misuse. Because the use, the conditions of use, product or product composition, and/or applicable laws may differ from one location to another and/or may change with time, the purchaser and/or user is solely responsible for determining whether the product is appropriate for use. McGean recommends use of this product solely in commercial processes which are specified by McGean and which do not violate any third-party patent rights or any laws or regulations or otherwise adversely impact human health and the environment. Users must make their own investigations and determine the suitability of the product for their particular purposes. McGean does not guarantee the accuracy of any data provided by its suppliers. MCGEAN MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE EXCEPT AS EXPRESSLY STATED IN THE SELLER'S SALES CONTRACT OR SALES ACKNOWLEDGEMENT FORM. USE OF ANY MCGEAN PRODUCT IS AT THE USER'S RISK.

Contact Us

United States
 McGean
 Phone: +1-216-441-4900
 Fax: +1-216-441-1377

United Kingdom
 McGean UK
 Phone: +44-1902-456563
 Fax: +44-1902-457443

Singapore
 McGean Singapore
 Phone: +65-6863-2296
 Fax: +65-6863-2297