



Penetrant Professor Approved

# Product Data Sheet FP-95A(M) Fluorescent Penetrant



Met-L-Chek manufactures a complete line of penetrants used in the fluorescent (Type 1) and visible (Type 2) dye penetrant inspection process. All Met-L-Chek penetrants are qualified to AMS-2644 and are sold under the Met-L-Chek® and Pen-Chek® trademarks.

FP-95A(M) is approved to AMS-2644 as a fluorescent (Type 1); Methods “B”, “C”, and “D”; sensitivity level 3 post emulsifiable inspection penetrant. It is approved with Method “B” emulsifier E-57 and Method “D” emulsifier E-58D. For Method “C” applications it is used with E-59, E-59A, R-503, and R-504. FP-95A(M) is applied by immersion, spray, or wipe on. FP-95A(M) meets requirements for high sensitivity aerospace applications.


FP-95A(M) is listed on the Qualified Products List for AMS-2644. It meets the requirements of AMS-2647, ASME Boiler and Pressure Vessel Code Section V, ASTM E-165, and ASTM E-1417, for penetrant inspection materials. It is low in sulfur and halogens and is safe for use on all metal surfaces.

### Guide to METHOD “B” (lipophilic) processing per ASTM E-1417

1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°-125°F) before penetrant is applied.
2. Apply FP-95A(M) using spray, immersion, or wipe on.
3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
4. Immerse part in and out of E-57 emulsifier, or flow on emulsifier; drain time < 3 minutes.
5. Wash part; water temperature 10°-38°C (50°-100 °F). Water pressure < 275kPa (< 40 psi); if a hydro-air nozzle is used limit pressure to < 172kPa (<25 psi). Distance >30cm (>12 inches). Wash time- only long enough to remove surface fluorescence under UV-A .
- 6\*. Dry part; temperature not to exceed 71°C (160°F), time - only long enough to dry surface.
7. Apply dry powder developer, form “a” (D-72A), by dusting, or non aqueous developer, form “d”(D-70), by spraying.
- 7A\*. If water based developers forms “b”(D-76B) or “c”(D-78B) are used they are applied by immersion or spray, prior to step 6 drying.
8. Wait a minimum of 10 minutes before inspection. Maximum time is 1 hour for form “d ” (non aqueous), maximum 2 hours for forms “b & c” (aqueous), and maximum 4 hours for form “a” (dry powder). If times are exceeded, clean part and reprocess.
9. Use UV-A illumination of >1000 μw/cm<sup>2</sup> @ 15inches (38.1 cm) in a darkened area of <21 lux visible light (<2 foot candles).

### Guide to METHOD “D” (hydrophilic) processing per ASTM E-1417

1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°-125°F) before penetrant is applied.
2. Apply FP-95A(M) penetrant using spray, immersion, or wipe on
3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
4. Pre-rinse part with water. Water temperature 10°-38°C (50°-100 °F). Water pressure < 275kPa (< 40 psi);only long enough to remove bulk of surface penetrant. This step may be skipped when emulsifier is applied by spray.
5. Immerse part in gently agitated E-58D emulsifier diluted to 17-20%. for 30 seconds to 2 minutes depending upon part roughness For spray applications emulsifier concentration should be 1-5% and spray contact for less than 2 minutes.
6. Wash part; water temperature 10°-38°C (50°-100 °F). Water pressure < 275kPa (< 40 psi); if a hydro-air nozzle is used limit pressure to < 172kPa (<25 psi). Distance >30cm (>12 inches). Wash time- only long enough to remove surface fluorescence under UV-A .
- 7\*. Dry part; temperature not to exceed 71°C (160°F), time - only long enough to dry surface.
8. Apply dry powder developer, form “a” (D-72A), by dusting, or non aqueous developer, form “d”(D-70), by spraying.
- 8A\*. If water based developers forms “b” (D-76B) or “c”(D-78B) are used they are applied by immersion or spray, prior to step 6 drying.
9. Wait a minimum of 10 minutes before inspection. Maximum time is 1 hour for form “d ” (non aqueous), maximum 2 hours for forms “b & c” (aqueous), and maximum 4 hours for form “a” (dry powder). If times are exceeded, clean part and reprocess.
10. Use UV-A illumination of >1000 μw/cm<sup>2</sup> @ 15inches (38.1 cm) in a darkened area of <21 lux visible light (<2 foot candles).



Fluorescent Penetrant Indications  
Type 1 (FP-95A(M),  
Method D (E-58D), Level 3,  
form “a”(D-72A).



Penetrant Professor Approved

# Product Data Sheet FP-95A(M) Fluorescent Penetrant



### Typical Physical Properties

Form: yellow green liquid  
 Density: 932 g/L  
 Flash Point: > 93°C (> 200°F)  
 Viscosity 6.9 mm<sup>2</sup>/s  
 Fluorescent Brightness: (AMS-2644 requirement > 90%): 95.3 %  
 Corrosion of aluminum: none  
 Corrosion of carbon steel: none  
 Corrosion of magnesium: none  
 Corrosion of stainless steel: none  
 Corrosion of titanium: none  
 Chloride content: < 100 ppm (0.01%)  
 Fluoride content: < 50 ppm (0.005%)  
 Sodium content: < 100 ppm (0.01%)  
 Sulfur content: < 100 ppm (0.01%)  
 Mercury: none  
 VOC's: 0 g/L  
 Ozone layer depleting substances: none  
 PCB's: none

### Specifications

**ISO-3452**  
**AMS-2644**                      **AMS-2647**  
**ASTM E-165**                    **ASTM E-1417**  
**BAC 5423**                      **GE P3TF2**  
**RR RPS-702-7**                **R-R Omat # 651D**  
**P&W PMC #4353**  
**Snecma sensibilité S3**  
**ASME B & PV code Sec V**

### Product Availability

6 x 1 pint (0.4L) can with dauber  
 1 gallon (3.7L) plastic bottle  
 5 gallon (18.9L) plastic jug with our spout  
 55 gallon (208L) plastic drum

### NSN #

1 gallon	6850-01-117-2971
1 gallon	6850-01-263-9774
1 gallon	6850-01-585-6425
1 gallon	6850-01-268-6705
5 gallon	6850-01-268-6700
5 gallon	6850-01-263-8432
5 gallon	6850-01-268-6706
55 gallon	6850-00-782-2736
55 gallon	6850-01-263-8433
55 gallon	6850-01-414-7086



BEFORE USING ANY OF THESE PRODUCTS, YOU MUST BECOME COMPLETELY FAMILIAR WITH THE INFORMATION CONTAINED IN MCGEAN'S SAFETY DATA SHEETS. All information contained therein or in this document regarding handling, personal protection, and other safety measures must be followed during use. McGean presents the information herein without warranty and disclaims any liability, including any consequential, special, or indirect damages, arising from its use and misuse. Because the use, the conditions of use, product or product composition, and/or applicable laws may differ from one location to another and/or may change with time, the purchaser and/or user is solely responsible for determining whether the product is appropriate for use. McGean recommends use of this product solely in commercial processes which are specified by McGean and which do not violate any third-party patent rights or any laws or regulations or otherwise adversely impact human health and the environment. Users must make their own investigations and determine the suitability of the product for their particular purposes. McGean does not guarantee the accuracy of any data provided by its suppliers. MCGEAN MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE EXCEPT AS EXPRESSLY STATED IN THE SELLER'S SALES CONTRACT OR SALES ACKNOWLEDGEMENT FORM. USE OF ANY MCGEAN PRODUCT IS AT THE USER'S RISK.

### Contact Us

United States  
 McGean  
 Phone: +1-216-441-4900  
 Fax: +1-216-441-1377

United Kingdom  
 McGean UK  
 Phone: +44-1902-456563  
 Fax: +44-1902-457443

Singapore  
 McGean Singapore  
 Phone: +65-6863-2296  
 Fax: +65-6863-2297